

#### US006007845A

## **United States Patent** [19]

## Domb et al.

# [11] **Patent Number:** 6,007,845

## [45] **Date of Patent:** \*Dec. 28, 1999

#### [54] NANOPARTICLES AND MICROPARTICLES OF NON-LINEAR HYDROPHILIC-HYDROPHOBIC MULTIBLOCK COPOLYMERS

[75] Inventors: **Abraham J. Domb**, Efrat, Israel; **Ruxandra Gref**, Nancy, France;

Yoshiharu Minamitake, Gumma, Japan; Maria Teresa Peracchia, Parma, Italy; Robert S. Langer, Newton,

Mass.

[73] Assignee: Massachusetts Institute of

**Technology**, Cambridge, Mass.

[\*] Notice: This patent is subject to a terminal dis-

claimer.

[21] Appl. No.: **08/582,993** 

[22] PCT Filed: Jul. 22, 1994

[86] PCT No.: PCT/US94/08287

§ 371 Date: **Jan. 22, 1996** 

§ 102(e) Date: Jan. 22, 1996

[87] PCT Pub. No.: WO95/03356

PCT Pub. Date: Feb. 2, 1995

428/402.24

428/402.21, 402.24, 403

## [56] References Cited

#### U.S. PATENT DOCUMENTS

4,501,726	2/1985	Schröder et al
4,757,128	7/1988	Domb et al
4,789,724	12/1988	Domb et al
4,801,739	1/1989	Franz et al
4,857,311	8/1989	Domb et al
4,888,176	12/1989	Langer et al 424/426
4,904,479	2/1990	Illum
5,133,908	7/1992	Stainmesse et al
5,141,739	8/1992	Jung et al 424/4
5,145,684	9/1992	Liversidge et al
5,149,543	9/1992	Cohen et al
5,410,016	4/1995	Hubbell et al 528/354
5,565,215	10/1996	Gref et al 424/503
5,578,325	11/1996	Domb et al 424/503

#### FOREIGN PATENT DOCUMENTS

0 092 918	11/1983	European Pat. Off
0 166 596	1/1986	European Pat. Off
0 295 055	12/1988	European Pat. Off
0 520 888 A1	6/1992	European Pat. Off
0 520 889 A1	6/1992	European Pat. Off
0 552 802	7/1993	European Pat. Off
WO 94/02122	2/1994	WIPO .

#### OTHER PUBLICATIONS

Agostini, S., "Synthesis and Characterization of PHB," Ph.D. thesis Case Western University, U.S.A. (1971).

Allen, T.M. and Hansen, C., "Pharmacokinetics of stealth versus conventional liposomes: effect of dose," Biochimica et *Biophysica Acta*, 1068: 133–141 (1991).

Allen, T.M., et al., "Liposomes containing synthetic lipid derivatives of poly(ethylene glycol) show prolonged circulation half–lives in vivo," *Biochimica et Biophysica Acta*, 1066: 29–36 (1991).

Deng, X.M., et al., J. of Polymer Science: Part C: Polymer Letters, 28: 411–416 (1990).

Illum., L. and Davis, S.S., "The organ uptake of intravenously administered colloidal particles can be altered by using a non-ionic surfactant (Poloxamer 338)," *FEBS Lett.* 1212, 167(1): 79–82 (1984).

Klibanov, A., et al., "Activity of amphipathic poly(ethylene glycol) 5000 to prolong the circulation time of liposomes depends on the liposome size and is unfavorable for immunoliposome binding to target," *Biochimica et Biophysics Acta*, 1062: 142–148 (1991).

Lasic, D.D., et al., "Sterically stabilized liposomes: a hypothesis on the molecular origin of the extended circulation times," *Biochimica et Biophysica Acta*, 1070: 187–192 (1991).

Maruyama, K., et al., "Effect of Molecular Weight in Amphipathyic Polyethyleneglycol on Prolonging the Circulation Time of Large Unilamellar Liposomes," *Chem. Pharm. Bull.*, 39(6): 1620–1622 (1991).

(List continued on next page.)

Primary Examiner—Lynette R. F. Smith Assistant Examiner—Datquan Lee Attorney, Agent, or Firm—Arnall Golden & Gregory, LLP

## [57] ABSTRACT

Particles are provided that are not rapidly cleared from the blood stream by the macrophages of the reticuloendothelial system, and that can be modified to achieve variable release rates or to target specific cells or organs. The particles have a core of a multiblock copolymer formed by covalently linking a multifunctional compound with one or more hydrophobic polymers and one or more hydrophilic polymers, and contain a biologically active material. The terminal hydroxyl group of the poly(alkylene glycol) can be used to covalently attach onto the surface of the particles biologically active molecules, including antibodies targeted to specific cells or organs, or molecules affecting the charge, lipophilicity or hydrophilicity of the particle. The surface of the particle can also be modified by attaching biodegradable polymers of the same structure as those forming the core of the particles. The typical size of the particles is between 180 nm and 10,000 nm, preferably between 180 nm and 240 nm, although microparticles can also be formed as described herein. The particles can include magnetic particles or radiopaque materials for diagnostic imaging, biologically active molecules to be delivered to a site, or compounds for targeting the particles. The particles have a prolonged halflife in the blood compared to particles not containing poly(alkylene glycol) moieties on the surface.

## 38 Claims, 7 Drawing Sheets